

# BDMA

## General Description

BDMA catalyst promotes the urethane reaction and is commonly used in high-water rigid foam applications to reduce friability

## Product Property

Reduced friability

## Applications

Standard catalyst for rigid foam applications.

## Typical Physical Property

Appearance	Colorless liquid
Flash Point, °C (PMCC)	54
Viscosity at 25°C	90
Specific Gravity at 25°C [g/cm]	0.91
Water Solubility	Partially soluble
Calculated OH number [mgKOH/g]	0

## Storage and package Information

HeJia Chemical recommends that our catalysts be stored in a dry and cool area under appropriate ventilation conditions. Each container should be closed tightly to avoid contamination with moisture or other negative influences, which could change the products' performance in the end use. And it can be stored 12 months at least. 180kgs per steel drum.

## Shelf Life

18 months from the date of production

## Disclaimer

The information contained in this TDS is believed to be accurate to the best of Hejia Chemical's knowledge and belief at the time of the TDS publication. The information is intended to be used as a guideline and for informational purpose only. Consequently we do not warrant that the information or the related products are fit for any particular purpose or use by users and it is user's responsibility to test and confirm the fitness of the product.

Hejia shall NOT BE LIABLE, whether contractually or in tort, for damages caused through the use or the reliance on this information and/or the related products.