

Technical Information

TEGOSTAB® B 84705

Description

TEGOSTAB® B 84705 is a non-hydrolysable polyether polydimethylsiloxane copolymer which is used in the manufacturing process of polyurethane rigid foam.

Key performance benefits

- Good stabilization
- Minimizing foam defects
- Especially suitable for winter formulations

Typical properties*

Appearance	Clear liquid
Viscosity at 25 °C	350 mPa · s
Density at 25 °C	1.06 g/cm ³
Calculated OH number	< 10 mg KOH/g

* For actual ranges, please refer to the Certificate of Analysis (CoA) / Sales Specification.

Application

TEGOSTAB® B 84705 is well suitable for one-component foam either for gun- or straw applications. It was primarily designed to achieve a very strong stabilization support which is a precondition for a fine cell-structured foam.

In case additional cell opening is needed in OCF, TEGOSTAB® B 84705 may be used in conjunction with a cell opener from the TEGOSTAB® or ORTEGOL® range.

Common use levels of TEGOSTAB® B 84705 in OCF are in the range of 3.0 and 6.0 parts per 100 parts of polyol. The optimal concentration will depend on specifics of the formulation.

Storage recommendations

- Shelf life: minimum 12 months. For exact date of expiration, please consider CoA.
- Storage conditions: dry and cool place in factory-packed containers.
- Solidification point: above 10 °C.
- Hence, storage temperature around 0 °C does not cause any deterioration of the material apart from the usual increase of the viscosity with falling temperatures. Nevertheless, it is recommended to bring the material to room temperature prior to use.

Safety instructions

Please consult the Safety Data Sheet for summary of product hazards, personal protective measures, and emergency release procedures.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Evonik Operations GmbH
Rellinghauser Straße 1–11
45128 Essen, Germany
Phone: +49 201 173 3006
Email: polyurethane@evonik.com



For any further information, contact either your regional sales or technical support or visit our customer portal explorepu.evonik.com.